Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2018-04-10-03** **Date: 13-04-18**
Customer	:	Assistant Executive Engineer, Vidyaranyapura Sub Division, BBMP, Bangalore.
Address	:	Vidyaranyapura Sub Division, BBMP, Bangalore.
Project Name	:	Improvements to roads and drains and other works in Kuvempunagara 2nd Stage Cross road and Surroundings in ward No.11 Kuvempunagara.
Agency	:	Executive Engineer, KRIDL, #280, 59th Cross road, 17th 'C' Main road, 3rd 'Y' Block, Rajajinagara, Bangalore-560 010.
Customer's Reference	:	BBMP/EE/BTP/WO/148/2017-18
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	10-04-18
Sample ID No	:	2018-04-10-03 /02(a)
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	10-04-18

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	315	315	2.1	97.9	90-100
3	20 mm	6985	7300	48.7	51.3	30-70
4	10 mm	4988	12288	81.9	18.1	10-35
5	4.75 mm	2245	14533	96.9	3.1	0-5
6	Pan	467	15000	100.0	0	---

CIVIL PRO Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2018-04-10-03** **Date: 13-04-18**

Sample ID No : 2018-04-10-03 /02(a)

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	10.8	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	11.6	
3	Specific Gravity	2.63	_
4	Bulk Density(Loose) (Kg/l)	1.43	_
5	Bulk Density(Compacted) (Kg/l)	1.47	_
6	Water Absorption(%)	0.21	_

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 90 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R KARTHIK RECHAN
Authorized Signatory
Quality Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com